



### EPOPLEX LS90 - RETROREFLECTIVITY ON DELAWARE SR-1

**Project location:** SR 1 near Dover, Delaware  
**Owner:** State of Delaware  
**Installation date:** December 9, 2002  
**Surface preparation:** 100% removal by grinding  
**Ambient temperature:** 32° F.  
**Surface temperature:** 27° F.  
**Cure time:** 15-17 minutes  
**Material Used:** Epoplex LS90 Polyurea  
**Glass beads used:** Cataphote type IV virgin glass 80% round, M-247 recycled glass 75% round  
**Installer:** Century Fence Company  
**Surface:** Concrete  
**Data collected by:** Delaware DOT  
**Date of last reading:** 12/02 – 1/04  
**Number of readings:** Unknown  
**Instrument used:** LTL 2000

